
ATC 500 S Series BMC Broadband Microwave Millimeter-wave 0603 NPO SMT Capacitors


- Low Insertion Loss
- Ultra High Self Resonance
- Surface Mountable
- Rugged Construction

ATC introduces the new 500 S Series Broadband Microwave Capacitor (BMC). This unique, patented component greatly exceeds both multilayer and single layer capacitor performance. It delivers extremely low insertion loss with ultra-high self resonance performance, in a rugged, laser-marked package compatible with automatic SMT manufacturing.


Functional applications include Broadband (Bypass, Coupling, Feedback, Impedance Matching, D.C. Blocking) and Tuning.



PARALLEL RESONANCE VS. CAPACITANCE



SERIES RESONANCE VS. CAPACITANCE





TECHNICAL

ATC Europe saleseur@atceramics.com

CERAMICS

ATC Asia sales@atceramics-asia.com



THE ENGINEERS' CHOICE™

www.atceramics.com

ATC 001-883 Rev. F; 2/08

ELECTRICAL AND MECHANICAL **SPECIFICATIONS**

QUALITY FACTOR (Q):

Greater than 1,000 @ 1 MHz.

TEMPERATURE COEFFICIENT OF CAPACITANCE (T.C.):

0 ±30 PPM/°C (-55°C to +125°C) (0.1 pF to 2.2 pF) $0 \pm 60 \text{ PPM/}^{\circ}\text{C} (-55^{\circ}\text{C to} + 125^{\circ}\text{C}) (2.4 \text{ pF to } 10 \text{ pF})$

INSULATION RESISTANCE (IR):

0.1 pF to 10 pF:

10⁵ Megohms min. @ +25°C @ rated WVDC. 10⁴ Megohms min. @ +125°C @ rated WVDC.

WORKING VOLTAGE (WVDC):

100 WVDC (0.1 pF to 4.7 pF) 50 WVDC (5.1 pF to 10 pF)

DIELECTRIC WITHSTANDING VOLTAGE (DWV):

200% of rated WVDC for 5 secs.

OPERATING TEMPERATURE RANGE:

From -55°C to $+125^{\circ}\text{C}$ (No derating of working voltage).

TERMINATION: Chip style suitable for surface mounting.

Platinum with gold flash.

Die Shear Strength Test per MIL-STD-883, Method 2019.

ENVIRONMENTAL TESTS

ATC 500 S Series Broadband Microwave Capacitors are designed and manufactured to meet and exceed the applicable requirements of MIL-C-55681.

THERMAL SHOCK:

MIL-STD-202, Method 107, Condition A.

MOISTURE RESISTANCE:

MIL-STD-202, Method 106.


LOW VOLTAGE HUMIDITY:

MIL-STD-202, Method 103, Condition A, with 1.5 Volts D.C. applied while subjected to an environment of 85°C with 85% relative humidity for 250 ±12 hours.

LIFE TEST:

MIL-STD-202, Method 108, for 2000 hours, at 125°C. 200% WVDC applied.

ATC 500 S SERIES BROADBAND 0603 CAPACITORS: MECHANICAL CONFIGURATIONS




MECHANICAL DIMENSIONS – INCHES (mm)								
Length (L)	L ₁	Width (W)	Thickness (T)	Gap (G)				
.060 ±.005 (1.52 ±.127)	.025 (.635) nom.	.030 ±.005 (.762 ±.127)	.024 (.609) max.	.010 (.254) min.				

TECHNICAL MERICAN CERAMICS **ATC Europe** ATC Asia


ATC North America sales@atceramics.com

saleseur@atceramics.com

sales@atceramics-asia.com



Frequency Range: 50 MHZ to 26.5 GHZ




Frequency (GHZ)

AMERICAN TECHNICAL CERAMICS


ATC North America sales@atceramics.com

ATC Europe saleseur@atceramics.com

ATC Asia sales@atceramics-asia.com



Frequency Range: 50 MHZ to 26.5 GHZ



Frequency (GHZ)

AMERICAN TECHNICAL CERAMICS

ATC North America sales@atceramics.com


ATC Europe saleseur@atceramics.com

ATC Asia sales@atceramics-asia.com

CAPACITANCE VALUES

CAP. CODE	CAP. (pF)	TOL.	RATED WVDC	CAP. CODE	CAP. (pF)	TOL.	RATED WVDC	CAP. CODE	CAP. (pF)	TOL.	RATED WVDC	CAP. CODE	CAP. (pF)	TOL.	RATED WVDC
0R1	0.1			1R1	1.1			3R0	3.0			6R8	6.8	C, J, K, M	
0R2	0.2			1R2	1.2			3R3	3.3	B, C, D		7R5	7.5		
0R3	0.3			1R3	1.3			3R6	3.6			8R2	8.2		
0R4	0.4			1R5	1.5		C, D 100	3R9	3.9		100	9R1	9.1		50
0R5	0.5	A, B,	400	1R6	1.6	B, C, D		4R3	4.3		C, D	100	10		1
0R6	0.6	C, D	100	1R8	1.8			4R7	4.7					K, M	
0R7	0.7	0, 5		2R0	2.0			5R1	5.1						
0R8	0.8			2R2	2.2			5R6	5.6		50				
0R9	0.9			2R4	2.4			6R2	6.2						
1R0	1.0			2R7	2.7										

ATC 500 SERIES BMC PART NUMBER CODE



The above part number refers to a 500S Series (case size S) 2.2 pF capacitor, B tolerance (±0.1 pF), Termination Code S (Platinum with gold flash), 100 WVDC, with marking and 5" tape and reel packaging.

ATC accepts orders for our parts using designations *with* or *without* the "ATC" prefix. Both methods of defining the part number are equivalent, i.e., part numbers referenced with the "ATC" prefix are interchangeable to parts referenced without the "ATC" prefix. Customers are free to use either in specifying or procuring parts from American Technical Ceramics.

For additional information and catalogs contact your ATC representative or call direct at (+1-631) 622-4700.

Consult factory for additional performance data.


AMERICAN TECHNICAL CERAMICS

ATC North America sales@atceramics.com


ATC Europe saleseur@atceramics.com

ATC Asia sales@atceramics-asia.com

3




Frequency Range: 50 MHZ to 26.5 GHZ




AMERICAN TECHNICAL CERAMICS ATC North America sales@atceramics.com ATC Europe ATC Asia sales@atceramics-asia.com

saleseur@atceramics.com www.atceramics.com



Frequency Range: 50 MHZ to 26.5 GHZ



Frequency (GHZ)

sales@atceramics-asia.com

A M E R I C A N T E C H N I C A L C E R A M I C S ATC North America ATC Europe ATC Asia

saleseur@atceramics.com
www.atceramics.com

sales@atceramics.com

Sales of ATC products are subject to the terms and conditions contained in American Technical Ceramics Corp. Terms and Conditions of Sale (ATC document #001-992 Rev. B 12/05). Copies of these terms and conditions will be provided upon request. They may also be viewed on ATC's website at www.atceramics.com/productfinder/default.asp. Click on the link for Terms and Conditions of Sale.

These drawings and specifications are the property of American Technical Ceramics, and any reproduction or disclosure in whole or in part as a basis for use in manufacture or sale of items is expressly prohibited without the written permission of American Technical Ceramics.

ATC has made every effort to have this information as accurate as possible. However, no responsibility is assumed by ATC for its use, nor for any infringements of rights of third parties which may result from its use. ATC reserves the right to revise the content or modify its product line without prior notice.

© 1998 American Technical Ceramics Corp. All Rights Reserved.

ATC 001-883 Rev. F; 2/08



TECHNICAL

ATC Europe
saleseur@atceramics.com

ERAMICSATC Asia
sales@atceramics-asia.com



THE ENGINEERS' CHOICE™

www.atceramics.com